



Development of dispersion procedures for surface-functionalized CuO nanoparticles to use in large-scale toxicity studies

Correia, Manuel; Ehrlich, Nicky; Fedutik, Yuri; Maltseva, Elena; Löschner, Katrin; Antipov, Alexei; Larsen, Erik Huusfeldt

Publication date:
2014

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):
Correia, M., Ehrlich, N., Fedutik, Y., Maltseva, E., Löschner, K., Antipov, A., & Larsen, E. H. (2014). *Development of dispersion procedures for surface-functionalized CuO nanoparticles to use in large-scale toxicity studies*. Abstract from NanoSafety Forum for Young Scientists, Syracuse, Italy, Syracuse, Italy.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Abstract -Nanosafety Forum for Young Scientists (8-9th October 2014, Sicily)

Participant: Manuel Correia

Affiliation: Technical University of Denmark, National Food Institute

Session 1: Materials

Development of dispersion procedures for surface-functionalized CuO nanoparticles to use in large-scale toxicity studies

Manuel Correia^{a, #}, Nicky Ehrlich^{a, #}, Yuri Fedutik^b, Elena Maltseva^b, Katrin Loeschner^a, Alexei Antipov^b and Erik H. Larsen^a

^a Technical University of Denmark, National Food Institute, DK-2860 Søborg, Denmark,

^b PlasmaChem GmbH, Rudower Chaussee 29, D-12489, Berlin, Germany;

[#] contributed equally to this work

CuO engineered nanomaterial (ENM) is widely used (e.g. biocide in textiles) and is highly toxic compared to other metal oxide ENM and bulk CuO¹. Industrial ENM production often yields agglomerated/sintered nanoparticles in the nanopowder product²⁻³. Since ENM toxicity depends greatly on particle size and surface composition, it is relevant for toxicity studies to develop dispersion procedures that result in stable and monodisperse ENM aqueous suspensions. The aim of this study was to compare dispersion techniques for CuO ENM for later use in a wide range of toxicity studies⁴.

CuO ENM was synthesized by pyrolysis and subjected to dispersion by ball-milling with ZrO₂ beads in aqueous or dilute acetic acid suspensions, or to dispersion in water by ultrasound probe sonication. Milling in diluted acetic acid resulted in monodispersed ENM with smaller mean hydrodynamic diameters compared with the other techniques. Acetic acid treatment led to CuO-clusters/ions release into the solution, as verified by inductively coupled plasma mass spectrometry (ICP-MS) analysis of ENM filtrates. Imaging by transmission electron microscopy (TEM) showed that the probe sonicated ENM suspensions were composed of aggregates of varying sizes, but with constituent nanostructures below 100 nm.

Ball-milling in acetic acid can introduce artifacts that would affect toxicity studies, e.g. release of Cu-ions or defects on the CuO crystal structure. Therefore, the probe sonication procedure was further applied to disperse pristine and functionalized (CH₃NH₂⁺ or COO⁻) CuO ENM variants.

Calibration of the ultrasound probe by calorimetry³ enables that similar ENM suspensions can be obtained across laboratories using different equipments.

References:

1. Cronholm P, Karlsson HL, Hedberg J, Lowe TA, Winnberg L, Elihn K, Wallinder IO, Möller L. Intracellular uptake and toxicity of Ag and CuO nanoparticles: a comparison between nanoparticles and their corresponding metal ions. *Small*. 2013 Apr 8;9(7):970-82.
2. Chapter 5 - Characterization methods for nanostructure of materials, In *Nanoparticle Technology Handbook* (Second Edition), edited by Hosokawa M, Nogi K, Naito M and Yokoyama T. Elsevier, Amsterdam, 2012, Pages 267,269-315, ISBN 9780444563361.
3. Taurozzi J, Hackley V, Wiesner M. Preparation of nanoparticle dispersions from powdered material using ultrasonic disruption. National Institute of Standards and Technology. 20A2. Available at: <http://nvlpubs.nist.gov/nistpubs/specialpublications/nist.sp.A200-2.pdf>.
4. Biological Foundation for the Safety Classification of Engineered Nanomaterials (ENM): Systems Biology Approaches to Understand Interactions of ENM with Living Organisms and the Environment (NanoSolutions) (European Union grant agreement no: 309329).